

Pressure-sensitive adhesives

Acrylic

Acrylic

Paper

TECHNI-THERM SP / TP170 @ 1.3 Cwt. / 40#SCK L-10

ITEM #73037

Facestock

A coated one side thermal transfer facestock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This facestock also offers an 86% brightness and an 87% opacity.

Type

Paper

Tensile MD

26 Lbs/in

Tear MD

42 Grams

Tensile CD

18 Lbs/in

Tear CD

42 Grams

Properties	Value
Caliper	2.70 Mil
Opacity	87

Regulatory Approval

Brightness

REACH
Yes
UL
No

86

FSC No

*Please contact your sales representative for details

Adhesive

A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Composition	Туре	Shear
Acrylic	Permanent	300
Application Townsysture	Min Application Townsonstons	BB - B - P - P - T
Application Temperature	Min. Application Temperature	Max. Application Temperature

Properties	Value		
Stainless Steel	5.2 lbs/linear in.		
Glass	3.2		
Polyethylene	1.6		
Corrugated	1.40 lbs./in.		
Painted Metal	5.2 lbs/linear		
Loop Tack	2.20 lbs./in2		
Regulatory Approval			
RoHS	Prop65	REACH	
Yes	No	Yes	
ТРСН	CPSIA	UL	
Yes	Yes	No	
Direct Food	Indirect Food		
No	Yes		

Adhesive

TPCH

*Please contact your sales representative for details

A general purpose patterned acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Composition Acrylic	Type Permanent	Shear 300
Application Temperature 35 F	Min. Application Temperature -65 F	Max. Application Temperature 180 F
Properties	Value	
Stainless Steel	5.2 lbs/linear in.	
Glass	3.2	
Polyethylene	1.6	
Corrugated	1.40 lbs./in.	
Painted Metal	5.2 lbs/linear	
Loop Tack	2.20 lbs./in2	
Regulatory Approval		
RoHS Yes	Prop65 No	REACH Yes

UL

CPSIA

Yes	Yes	No
Direct Food	Indirect Food	
No	Yes	
*Please contact your sales representative for	details	

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Туре			
17142			
Tensile MD	Tensile CD		
34 Lbs/In	22 Lbs/In		
Tear MD	Tear CD		
32 Grams	34 Grams		
Description	Value		
Basis Weight	40 Lbs/Rm		
Caliper	2.5 Mil		
Regulatory Approval			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA	UL	
Yes	Yes	No	

No

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

800-358-4448

orders.us@beontag.com

^{*}Please contact your sales representative for details