

Pressure-sensitive adhesives

Hot Melt

Film

# TECHNIFLEX / AP151 @ 1.3 Cwt. / 40#SCK L-3

ITEM #151527

#### **Facestock**

A 3.5 mil white polyolefin label film for pressure sensitive applications that offers excellent moisture resistance, stain resistance, dimensional stability and squeezability.

Туре

Film

Tensile MDTensile CD34000 Psi18000 Psi

**Tear MD** 37 Grams

**Opacity** 

**Elong MD**500
Elong CD
40

Properties Value

Caliper 3.50 Mil

#### **Regulatory Approval**

RoHSProp65REACHYesYesYes
TPCH
CPSIA
FSC
Yes
No

85

## Adhesive

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

<b>Composition</b> Hot Melt	<b>Type</b> Permanent	Shear 80
<b>Application Temperature</b> 35 F	<b>Min. Application Temperature</b> -65 F	<b>Max. Application Temperature</b> 220 F
Properties	Value	

<sup>\*</sup>Please contact your sales representative for details

**Stainless Steel** 7.3 lbs/linear in.

Glass 5.7

Polyethylene 6.5

Corrugated 2.50 lbs./in.

Painted Metal 7.0 lbs/linear in.

**Loop Tack** 5.00 lbs./in.

## **Regulatory Approval**

RoHS<br/>YesProp65<br/>NoREACH<br/>YesTPCHCPSIAUL

Yes

Direct Food Indirect Food

No Yes

#### Liner

Yes

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

No

## Туре

5517342

32 Grams

Caliper

Tensile MD

34 Lbs/ln

Tear MD

Tensile CD

22 Lbs/ln

Tear CD

Description Value

Basis Weight 40 Lbs/Rm

## **Regulatory Approval**

RoHS<br/>YesProp65<br/>YesREACH<br/>YesTPCH<br/>YesCPSIA<br/>YesUL<br/>No

2.5 Mil

34 Grams

#### **Direct Food**

No

Last update: 05/01/2024

<sup>\*</sup>Please contact your sales representative for details

<sup>\*</sup>Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS: Beontag 222 Mound Avenue Miamisburg, OH 45342

800-358-4448 orders.us@beontag.com