

TYVEK / TS583 @ 2.10 Cwt. / 50#SCK L-3

ITEM #4785

Facestock

A durable sheet that is stronger than paper, less expensive and more versatile than fabrics. It is made from high density polyethylene fibers and is considered a spunbonded olefin offering a balance of physical characteristics likened to a paper, film and cloth.

Type

Film

Tensile MD

42 Lbs/in

Tensile CD

48 Lbs/in

Tear MD

453 Grams

Tear CD

453 Grams

Elong MD

20

Elong CD

24

Properties

Value

Caliper

8.00 Mil

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

*Please contact your sales representative for details

Adhesive

A specialty adhesive designed to adhere to hard to label surfaces with excellent ultimate adhesion when applied at temperatures as low as -20 F. Outstanding permanency at room temperatures. This adhesive has good plasticizer, UV & solvent resistance and high initial tack.

Type

Permanent

Composition

Acrylic

Shear

70

Application Temperature

-20 F

Min. Application Temperature

-65 F

Max. Application Temperature

160 F

Properties

Value

Stainless Steel

5.9 lbs/linear in.

Glass	4.2	
Polyethylene	4.1	
Corrugated	1.50 lbs./in.	
Painted Metal	5.1 lbs/linear in.	
Loop Tack	3.20 lbs./in ²	
Regulatory Approval		
RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No	Indirect Food Yes	
*Please contact your sales representative for details		

Liner Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
Type 5517353		
Tensile MD 40 Lbs/In	Tensile CD 24 Lbs/In	
Tear MD 44 Grams	Tear CD 48 Grams	
Description	Value	
Basis Weight	50 Lbs/Rm	
Caliper	3.2 Mil	
Regulatory Approval		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com