

FSC ScandCoat MC PB SSP 50N x 2 HG0 x 2



Description

This is a PiggyBack construction that has two release coated backing papers, two layers of adhesive and a face material which allows a label to be applied, complete with backing, for future or further application.

The values indicated in this leaflet are not intended to be a specification but a guide to the values that may generally be expected. Customers should independently determine, prior to use, the suitability of any material for a specific purpose. All information is subject to change without notice.

Facestock

ScandCoat MC is a medium gloss machine coated paper with good whiteness. It is a versatile paper which is suitable for a very wide range of primary label work. Developed for general colour printing, ScandCoat MC gives good colour lift and can be printed by flexography, rotary or flat-bed letterpress, offset lithography, screen process and can be foil blocked and varnished. It can also be thermal transfer overprinted with suitable smudge resistant ribbons.

This is a PiggyBack construction that has two release coated backing papers, two layers of adhesive and a face material which allows a label to be applied, complete with backing, for future or further application.

Type

Paper

Properties	Method	Value
Basis Weight	ISO 536	78 ± 3g/m ²
Caliper	ISO 534	68 ± 5µ
Opacity	ISO 2471	0.89
Brightness	ISO 11475	1.2

Regulatory Approval

FSC

Yes

Adhesive

ScandStick Permanent 50N has excellent initial tack with high bond strength at elevated, room and chilled temperatures, as well as in moist conditions. It has been formulated to adhere to a wide variety of substrates, including corrugated cardboard, low surface energy materials like polyethylene and non-polar surfaces. SSP 50N provides enhanced conversion characteristics, allowing die-cutting at higher speeds and is designed for both paper and synthetic face materials. Limitation: Not suitable for labelling plasticised PVC.

General purpose chill permanent

Type

Permanent

Composition

Hot Melt

Composition

SSP 50N

Min. Application Temperature

Min. Service Temperature

Max. Service Temperature

Regulatory Approval

Direct Food

Yes

Indirect Food

Yes

Food contact

Meets composition requirement of indirect food additives regulation FDA175.105, BfR XIV.

ISEGA approved for direct contact with dry and moist non-fatty foods

Yes

Backing

HG0 honey glassine backing allows high speed conversion and consistent dispensing on a wide range of equipment.

Type

Paper

Description

Method

Value

Caliper

ISO 534

49 ± 3μ

Transparency

ISO 2469

0.5

Final product

Description

Value

Typical Caliper

182 ± 20μ

Min. Application Temperature

-5°C

Min. Service Temperature

-40°C

Max. Service Temperature

70°C

Format

Roll

Certificate

The product is registered to SCS-COC-004802 FSC™ Mix credit.

Material Shelf Life

12 months stored at 20°C/50% RH

SKU

F120000J0P000

Last update: 01/05/2024

ADDRESS:

Beontag

Pål Anders väg 4, 263 35

Höganäs, Sweden

+46 42 25 00 50

orders.scandstick@beontag.com