

# FSC ScandTherm NTC SSP E60 HG0



## Description

The values indicated in this leaflet are not intended to be a specification but a guide to the values that may generally be expected. Customers should independently determine, prior to use, the suitability of any material for a specific purpose. All information is subject to change without notice.

### Facestock

Scandtherm NTC is a white, woodfree paper, with black imaging thermosensitive coating . It is designed for short term use in relatively clean and dry environments, where there are no requirements for surface protection against contaminants or scruffing. It can be printed with all commonly used technologies for roll converting, including water and uv-based flexo, uv letterpress et.c., if inks and varnishes designed for direct thermal paper is used. We recommend customers to assess both pre-print and thermal print characteristics under end-use conditions before proceeding to long runs. This thermal paper has a standard/high sensitivity, making it suitable for print speeds up to 250 mm/s, depending on printer settings. This product does not contain Bisphenol A.

### Type

Paper

Properties	Method	Value
Basis Weight	ISO 536	68 ± 5g/m²
Caliper	ISO 534	75 ± 5µ

### Regulatory Approval

BPA Free	FSC
Yes	Yes

### Adhesive

ScandStick SSP E60 is a highly versatile permanent adhesive which will adhere to a wide variety of surfaces, both at room temperature and under chill conditions. SSP E60 has been designed to resist edge lift on narrow radius tubes and curved surfaces. SSP E60 has excellent conversion characteristics ensuring consistent waste stripping and label dispensing. It is also suitable for on-press delamination to allow printing on the adhesive surface or tack neutralisation. Although SSP E60 will tolerate some surface condensation, excessive amount of moisture present will reduce the adhesion.

General purpose permanent

Type	Composition	Composition
Permanent	Acrylic	SSP E60
Min. Application Temperature	Min. Service Temperature	Max. Service Temperature
5°C	-20°C	100°C

Properties	Method	Value
Peel	FTM 1 (20 min)	13N
Tack	FTM 9	14N
<b>Regulatory Approval</b>		
<b>Direct Food</b> Yes	<b>Indirect Food</b> Yes	<b>Food contact</b> Meets composition requirement of indirect food additives regulation FDA175.105, BfR XIV.
<b>ISEGA approved for direct contact with dry and moist non-fatty foods</b> Yes		

<b>Backing</b> HG0 honey glassine backing allows high speed conversion and consistent dispensing on a wide range of equipment.		
<b>Type</b> Paper		
Description	Method	Value
Caliper	ISO 534	49 ± 3μ
Transparency	ISO 2469	0.5

<b>Final product</b>		
Description	Value	
Typical Caliper	133 ± 10μ	
<b>Min. Application Temperature</b> 5°C	<b>Min. Service Temperature</b> -20°C	<b>Max. Service Temperature</b> 100°C
<b>Format</b> Roll		
<b>Certificate</b> The product is registered to SCS-COC-004802 FSC™ Mix credit.		
<b>Material Shelf Life</b> 24 months stored at 20°C/50% RH		
<b>SKU</b> FB205000I0N000		

Last update: 01/05/2024

ADDRESS:

Beontag

Pål Anders väg 4, 263 35

Höganäs, Sweden

+46 42 25 00 50

[orders.scandstick@beontag.com](mailto:orders.scandstick@beontag.com)