

Self adhesives

Hot Melt

SSF 933

Paper

FSC ScandTherm TCS SSF 933 HG0



DESCRIPTION

The values indicated in this leaflet are not intended to be a specification but a guide to the values that may generally be expected. Customers should independently determine, prior to use, the suitability of any material for a specific purpose. All information is subject to change without notice.

FACESTOCK

ScandTherm TCS is a protected direct chemi-thermal label, which is a woodfree paper with a coating of thermosensitive dyes which turn black when heated. There is a top coating which protects the label surface and thermally printed images from above, against contaminants such as moisture, oil, grease and plasticisers from films. ScandTherm TCS can be printed by water based and UV inks and varnishes designed for use with direct thermal papers. This thermal paper has a standard sensitivity making it suitable for print speeds up to 200-250mm per second depending on printer settings. It is recommended that customers assess both the pre-print and the overprint characteristics under end use conditions before proceeding to long runs..

TypePaper

Top Coating

Yes

Image color Printing speed (Max.)

Black 200 mm/s

| PROPERTIES | METHOD | VALUE |
|--------------|---------|------------|
| Basis Weight | ISO 536 | 75 ± 5g/m² |
| Caliper | ISO 534 | 80 ± 8µ |

REGULATORY APPROVAL

FSC

Yes

ADHESIVE

SSF933 has excellent initial tack and adhesion on a wide variety of substrates, including apolar, slightly rough and curved substrates. SSF933 is specially designed for use at low temperature and freezer conditions. For applications on cardboard in temperatures warmer than 0 °C we recommend the SSP 50N or the SSP 713.

Deep freeze permanent

| Туре | Min. Application Temperature | Min. Service Temperature |
|-----------|------------------------------|--------------------------|
| Permanent | -20°C | -40°C |
| | | |

Max. Service Temperature

50°C

| PROPERTIES METHOD VALUE |
|-------------------------|
|-------------------------|

Peel FTM 1 (20 min) 5,5N

Tack FTM 9 12N

REGULATORY APPROVAL

Food contact

Meets composition requirement of indirect food additives regulation FDA 21-CRF 175.105

ISEGA approved for direct contact with dry and moist non-fatty foods

No

BACKING

HG0 honey glassine backing allows high speed conversion and consistent dispensing on a wide range of equipment.

Туре

Paper

| FINAL PRODUCT | |
|-----------------|-----------|
| DESCRIPTION | VALUE |
| Typical Caliper | 139 ± 10% |

Format

Roll

Certificate

The product is registered to SCS-COC-004802 FSC ™ Mix credit.

Material Shelf Life

12 months stored at 20°C/50% RH

Last update: 01/05/2024

ADDRESS: Beontag Pål Anders väg 4, 263 35 Höganäs, Sweden +46 42 25 00 50

orders.scandstick@beontag.com